



15301 Dixie Highway  
 Louisville, KY 40272  
 Telephone (502) 933-0122  
 FAX (502) 933-6334

**CEMENT  
 MILL  
 TEST  
 REPORT**

**Cement Identified as Type I, Type II HA Kosmos  
 Cement**  
**Location: Louisville, Kentucky**  
**Kosmos Cement Customers**  
**Sample Receiving and Testing**  
**Dates: October 1-30**

**Date: 11/14/2021**

**October**

STANDARD COMPOSITION REQUIREMENTS (ASTM C114)	ASTM C150 SPECIFICATIONS	TYPE I	TYPE II	TEST
Silicon Dioxide (SiO <sub>2</sub> ), %	---	---	---	18.0
Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> ), %	Maximum	---	6.0	4.8
Ferric Oxide (Fe <sub>2</sub> O <sub>3</sub> ), %	Maximum	---	6.0	3.2
Calcium Oxide (CaO), %	---	---	---	61.4
Magnesium Oxide (MgO), %	Maximum	6.0	6.0	4.0
Sulfur Trioxide (SO <sub>3</sub> ), %	Maximum	3.0	3.0	3.90 <sup>A</sup>
Loss on Ignition (LOI), %	Maximum	3.5	3.5	2.9
Insoluble Residue, %	Maximum	1.50	1.50	0.75
Alkalies (Na <sub>2</sub> O equivalent), %	---	---	---	0.57
Tricalcium Silicate (C <sub>3</sub> S),	---	---	---	62.4
Dicalcium Silicate (C <sub>2</sub> S), %	---	---	---	2.0
Tricalcium Aluminate (C <sub>3</sub> A), %	Maximum	---	8	6.9
(C <sub>3</sub> S+4.75C <sub>3</sub> A)	Maximum	---	100	95.2
Limestone %	Maximum	5	5	4.0
CO <sub>2</sub> %	---	---	---	1.90
CaCO <sub>3</sub> % in Limestone	Minimum	70	70	82
<b>STANDARD PHYSICAL REQUIREMENTS</b>				
(ASTM C204) Blaine Fineness, m <sup>2</sup> /kg	Minimum	280	280	403
(ASTM C430) -325 Mesh, %	---	---	---	95.4
(ASTM C191) Time of Setting (Vicat)	Minimum/Maximum	45/375	45/375	117
Initial Set, minutes	---	---	---	253
Final Set, minutes	Maximum	---	---	63.3 <sup>B</sup>
(ASTM C1702) Calorimetry	Minimum	50	50	88
(ASTM C451) False Set, % (Optional)	Maximum	12	12	7.3
(ASTM C185) Air Content, %	Maximum	0.80	0.80	0.107
(ASTM C151) Autoclave Expansion, %	---	---	---	26.2
(ASTM C187) Normal Consistency, %	---	---	---	---
(ASTM C109) Compressive Strength, psi (MPa)	Minimum	1740(12.0)	1450(10.0)	4180
3 Day - psi (MPa)	Minimum	2760(19.0)	2470(17.0)	5330
7 Day - psi (MPa)	---	---	---	---
28 Day - psi (MPa) (Optional)	---	---	---	---

• Kosmos Cement hereby certifies that this cement meets or exceeds the chemical and physical specifications of ASTM C150 and AASHTO M85 for TYPE I and TYPE II portland cement.

<sup>A</sup> In compliance with ASTM C150, since Optimum SO<sub>3</sub> exceeds 3.0%, the most recent results of ASTM C1038 for expansion in water at 14 days is <0.020%.

<sup>B</sup> The value for ASTM C1702 is in accord with the required testing frequency.

*Tom Kyser*

By:  
 Tom Kyser  
 Quality Control Manager  
 Kosmos Cement

Physical testing/sampling completed by: EO, DB  
 Chemical testing/sampling completed by: E.O, EW,



15301 Dixie Highway  
 Louisville, KY 40272  
 Telephone (502) 933-0122  
 FAX (502) 933-6334

**CEMENT  
 MILL  
 TEST  
 REPORT**

**Cement Identified as: Type I, Type II HA**  
**Plant: Kosmos Cement**  
**Cement Location: Louisville, Kentucky Kosmos**  
**Cement Customers**  
**Sample Receiving and Testing Dates: October 1-30**

**Date: 11/14/2021**

**October**

Additional Data Limestone					TEST
Silicon Dioxide (SiO <sub>2</sub> ), %					5.6
Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> ), %					0.80
Ferric Oxide (Fe <sub>2</sub> O <sub>3</sub> ), %					0.40
Calcium Oxide (CaO), %					45.7
Sulfur Trioxide (SO <sub>3</sub> ), %					0.15
Base Cement Composition					65.0
C3S %					2.1
C2S %					7.2
C3A %					9.7
C4AF %					None
Inorganic Processing Data					None

• Kosmos Cement hereby certifies that the above described data represents the materials used in the cement manufactured during the production period indicated

*Tom Kyser*

By:  
 Tom Kyser  
 Quality Control Manager  
 Kosmos Cement